

[MatWeb](#), The Online Materials Database

Aluminum 6063-T6

Subcategory: 6000 Series Aluminum Alloy; Aluminum Alloy; Metal; Nonferrous Metal

Close Analogs:

Composition Notes:

Aluminum content reported is calculated as remainder.

Composition information provided by the Aluminum Association and is not for design.

Key Words: UNS A96063; ISO AlMg0.5Si; Aluminium 6063-T6; AA6063-T6

Component	Wt. %	Component	Wt. %	Component	Wt. %
Al	Max 97.5	Mg	0.45 - 0.9	Si	0.2 - 0.6
Cr	Max 0.1	Mn	Max 0.1	Ti	Max 0.1
Cu	Max 0.1	Other, each	Max 0.05	Zn	Max 0.1
Fe	Max 0.35	Other, total	Max 0.15		

Material Notes:

Data points with the AA note have been provided by the Aluminum Association, Inc. and are NOT FOR DESIGN.

Physical Properties	Metric	English	Comments
Density	2.7 g/cc	0.0975 lb/in ³	AA; Typical
Mechanical Properties			
Hardness, Brinell	73	73	AA; Typical; 500 g load; 10 mm ball
Hardness, Knoop	96	96	Converted from Brinell Hardness Value
Hardness, Vickers	83	83	Converted from Brinell Hardness Value
Ultimate Tensile Strength	241 MPa	35000 psi	AA; Typical
Tensile Yield Strength	214 MPa	31000 psi	AA; Typical
Elongation at Break	12 %	12 %	AA; Typical; 1/16 in. (1.6 mm) Thickness
Modulus of Elasticity	68.9 GPa	10000 ksi	AA; Typical; Average of tension and compression. Compression modulus is about 2% greater than tensile modulus.
Ultimate Bearing Strength	434 MPa	62900 psi	Edge distance/pin diameter = 2.0
Bearing Yield Strength	276 MPa	40000 psi	Edge distance/pin diameter = 2.0
Poisson's Ratio	0.33	0.33	
Fatigue Strength	68.9 MPa	10000 psi	AA; 500,000,000 cycles completely reversed stress; RR Moore machine/specimen
Machinability	50 %	50 %	0-100 Scale of Aluminum Alloys

Shear Modulus	25.8 GPa	3740 ksi	
Shear Strength	152 MPa	22000 psi	AA; Typical

Electrical Properties

Electrical Resistivity	3.32e-006 ohm-cm	3.32e-006 ohm-cm	AA; Typical at 68°F
------------------------	------------------	------------------	---------------------

Thermal Properties

CTE, linear 68°F	23.4 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	13 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	AA; Typical; Average over 68-212°F range.
CTE, linear 250°C	25.6 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	14.2 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	Average over the range 20-300°C
Specific Heat Capacity	0.9 J/g $\cdot^\circ\text{C}$	0.215 BTU/lb $\cdot^\circ\text{F}$	
Thermal Conductivity	200 W/m $\cdot\text{K}$	1390 BTU-in/hr $\cdot\text{ft}^2\cdot^\circ\text{F}$	AA; Typical at 77°F
Melting Point	616 - 654 °C	1140 - 1210 °F	AA; Typical range based on typical composition for wrought products 1/4 inch thickness or greater
Solidus	616 °C	1140 °F	AA; Typical
Liquidus	654 °C	1210 °F	AA; Typical

Processing Properties

Annealing Temperature	413 °C	775 °F	hold at temperature for 2 to 3 hr; cool at 50°F per hour from 775 to 500°F
Solution Temperature	521 °C	970 °F	
Aging Temperature	177 °C	350 °F	hold at temperature for 8 hr

References are available for this material.

Copyright 1996-2007 by Automation Creations, Inc. The information provided by MatWeb is intended for personal, non-commercial use. The contents, results, and technical data from this site may not be reproduced either electronically, photographically or substantively without permission from Automation Creations, Inc. No warranty, neither expressed nor implied, is given regarding the accuracy of this information. The user assumes all risk and liability in connection with the use of information from MatWeb.